

EUCOPATCH

SINGLE COMPONENT, RAPID SETTING REPAIR MATERIAL

DESCRIPTION

EUCOPATCH is a single-component, rapid-setting, repair mortar for use on new and existing concrete and masonry surfaces. This product is designed for the reconstruction of damaged vertical and overhead concrete and masonry structures, both interior and exterior. EUCOPATCH can also be used in light-duty, pedestrian, horizontal applications. The light color of EUCOPATCH closely resembles aged, sun-bleached concrete.

PRIMARY APPLICATIONS

- Walls
- Light-duty (pedestrian) pavements
- Curbs and gutters
- Precast panels
- Columns
- Masonry units

FEATURES/BENEFITS

- Rapid setting for repairs up to 4" (10 cm)
- High compressive strength
- Excellent resistance to freeze-thaw cycling and de-icing salts
- Suitable for both interior and exterior applications
- Excellent bond to sound concrete
- Compatible with galvanic anodes

TECHNICAL INFORMATION

Typical Engineering Data The following results were developed under laboratory conditions using 0.7 gal /50 lb bag (2.65 L/22.7 kg)

Set Times 70°F (21°C) ASTM C 266

Initial set 8 min

Final set 20 min

Bond Strength

28 days 1,400 psi (10 MPa)

Compressive Strength ASTM C 109 2" (50 mm) cubes
Age **Strength**

1 day 2,000 psi (14 MPa)

7 days 4,500 psi (31 MPa)

28 days 5,500 psi (38 MPa)

56 days 6,500 psi (45 MPa)

Volumetric Resistivity 3,270 ohm/cm

Appearance: EUCOPATCH is a free-flowing powder designed to be mixed with water. After mixing and placing, the color may initially appear darker than the surrounding concrete. This color will lighten up substantially as the EUCOPATCH cures, resulting in the repair area very closely matching the surrounding concrete.

PACKAGING/YIELD

EUCOPATCH is packaged in 50 lb (22.7 kg) bags which yield 0.44 ft³ (0.013m³) when mixed with 0.7 to 0.75 gal (2.65 to 2.81L) of water. EUCOPATCH is also available in 60 lb (27.2 kg) pails which yield 0.56 ft³ (0.016 m³) when mixed with 0.84 to 0.90 gal (3.2 to 3.4 L) of water.

SHELF LIFE

2 years in original, unopened package

COVERAGE

One 50 lb (22.7 kg) unit of EUCOPATCH will cover approximately 11.3 ft² (1.05 m²) when placed at an average depth of 1/2" (13 mm). One 60 lb (27.2 kg) unit of EUCOPATCH will cover approximately 13.6 ft² (1.26 m²) when placed at an average depth of 1/2" (13 mm).



The Euclid Chemical Company

19218 Redwood Rd. • Cleveland, OH 44110

Phone: [216] 531-9222 • Toll-free: [800] 321-7628 • Fax: [216] 531-9596

www.euclidchemical.com

An **RPM** Company



DIRECTIONS FOR USE

Surface Preparation: Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a minimum surface profile of CSP 5 - 7 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

Priming: Clean and prime exposed steel with DURALPREP AC. Concrete should be primed with a spray or brush coat of DURALPREP AC. The DURALPREP AC primer coating must be allowed to fully dry prior to the placement of EUCOPATCH. Alternately, a Saturated Surface Dry (SSD) concrete surface can be primed with a scrub coat of EUCOPATCH. The repair must be made before the scrub coat dries out.

Mixing: Single bags may be mixed with a drill and "jiffy" mixer. Use a paddle type mortar mixer for large jobs. All materials should be in the proper temperature range of 60°F to 90°F (16°C to 32°C). Add the appropriate amount of water for the batch size and then add the dry product. The mixed product should be quickly transported to the repair area and placed immediately.

Placement: Place EUCOPATCH onto the prepared concrete or masonry surface at a minimum depth of at least 1/16" (1.6mm). Float or trowel flush with adjacent surface and allow to set. Finish to match the surrounding surfaces. Place EUCOPATCH while the scrub coat is still wet.

Finishing: Finish the repair material to the desired texture. Do not add additional water to the surface during the finishing operation. Use EUCOBAR evaporation retarder.

Curing and Sealing: Proper curing procedures are important to ensure the durability and quality of the repair. To prevent surface cracking, cure the material with a high solids curing compound, such as SUPER AQUA-CURE VOX or SUPER REZ-SEAL. Allow the curing compound to dry. In hot, windy or direct sunlight situations, apply a second coat of curing compound. If a curing compound is not desired, wet cure for a minimum of three days.

CLEAN-UP

Clean tools and equipment with water before the material hardens.

PRECAUTIONS/LIMITATIONS

- Only mix as much material that can be used in 10 minutes.
- Do not use for a topping or overlay.
- For structural repairs of vertical and overhead surfaces, use VERTICOAT SUPREME or TAMMS STRUCTURAL MORTAR.
- Do not use material at temperatures below 45°F (7°C).
- Keep repair from freezing until a minimum strength of 1000 psi (7 MPa) is reached.
- Store product in a dry place.
- For high strength repairs of floors and pavements, use THIN-TOP SUPREME or CONCRETE-TOP SUPREME.
- In all cases, consult the Material Safety Data Sheet before use.

Rev. 06.11

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.