



DURALFLEX LV

LOW VISCOSITY, LOW MODULUS EPOXY ADHESIVE

PACKAGING

4 gal (15 L) unit (two 2 gal [7.5 L] kits)
Code: TD5344104520 (Concrete Gray)

CLEAN UP

Clean tools and application equipment immediately with acetone, xylene, or MEK. Clean spills or drips with the same solvents while still wet. Hardened DURALFLEX LV will require mechanical abrasion for removal.

SHELF LIFE

2 years in original, unopened package

SPECIFICATIONS AND COMPLIANCES

- Complies with ASTM C881 Type III, Grade 1, Class B and C

DESCRIPTION

DURALFLEX LV is a two-component, 100% solids, moisture insensitive, high strength epoxy adhesive and binder for numerous applications. This low modulus, low viscosity epoxy resin is the perfect solution for general bonding applications.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Exceptional adhesion to construction materials
- Easy to use 1:1 mix ratio
- Moisture insensitive
- Tenacious bond strength

PRIMARY APPLICATIONS

- Bonding of concrete, masonry or wood
- Mix with dried silica sand to create a repair mortar

APPEARANCE

Part A liquid is gray in color and Part B liquid is amber in color.

COVERAGE

1 neat gal (3.8 L) yields 231 in³ (3,785 cm³) of epoxy. 3 gal (11.4 L) of neat DURALFLEX LV epoxy mixed with 1 gal (3.8 L) of dry 20/40 mesh silica sand will yield approximately 643 in³ (10,537 cm³) of mortar.

Note: Coverage rates are approximate. Actual coverage depends on temperature, texture, and substrate porosity.

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Result
ASTM D2556	Mixed Viscosity	1,800 cp
ASTM C881	Gel Time	25 minutes
ASTM C882	Bond Strength	2 days: > 2,000 psi (13.8 MPa) 14 days: > 2,300 psi (15.9 MPa)
ASTM D570	Water Absorption	24 hours: < 0.5%
ASTM D695	Compressive Yield	7 days: > 5,000 psi (34.5 MPa)
ASTM D695	Compressive Modulus	7 days: 300,000 psi (2,068 MPa)
ASTM D638	Tensile Strength	7 days: > 2,000 psi (13.8 MPa)
ASTM D638	Elongation at Break	> 30%

DIRECTIONS FOR USE

Surface Preparation: The surface must be structurally sound, dry, clean and free of grease, oil, curing compounds, soil, dust and other contaminants. Surface laitance must be removed. Concrete surfaces must be roughened and made absorptive, preferably by mechanical means, and then thoroughly cleaned of all dust and debris. If the surface was prepared by chemical means (acid etching), a water/baking soda or water/ammonia mixture, followed by a clean water rinse, must be used for cleaning, in order to neutralize the substrate. Allow substrate to dry before application. Route cracks and blow dust/debris from them with oil-free compressed air. Following surface preparation, the strength of the surface can be tested if quantitative results are required by project specifications. An elcometer or similar tensile pull tester may be used in accordance with ASTM D4541, and the tensile pull-off strength should be at least 250 psi (1.7 MPa).

When coating steel, all contamination should be removed and the steel surface prepared to a "near white" finish (SSPC SP10) using clean, dry blasting media.

Mixing: Mix DURALFLEX LV using a low-speed drill and a mixing paddle. Pre-mix Part A and Part B separately for approximately 1 minute each. Combine Part A and Part B in a 1:1 ratio by volume, then mix thoroughly for 3 to 5 minutes. To make DURALFLEX LV mortar, gradually add clean, dry, 20/40 mesh silica sand to previously mixed DURALFLEX LV epoxy and mix thoroughly for 3 to 5 minutes. The mix ratio of mixed epoxy to aggregate is approximately 3:1 by volume, but can be modified depending on the desired consistency of the mortar.

Scrape the bottom and sides of the containers at least once during mixing. Do not scrape bottom or sides of the container once mixing operations have ceased; doing so may result in unmixed resin or hardener being applied to the substrate. Unmixed resin or hardener will not cure properly. Do not aerate the material during mixing. To keep aeration to a minimum, the recommended mixing paddles are #P1 or #P2 as found in ICRI Guideline 320.5R-2014.

Application: General bonding: Apply by roller, brush, or squeegee. Ensure the surfaces to be joined have uniform coatings of DURALFLEX LV. For optimum results, the bond line should not exceed 1/8" (3.2 mm). Join surfaces and hold or clamp firmly until the epoxy gels. Ideally, a small amount of adhesive should exude from the joint. Surfaces must be mated while the adhesive is still tacky. **Patching and repairs:** Apply DURALFLEX LV neat as a primer coat to the prepared concrete surface. Mix the DURALFLEX LV into an epoxy mortar and apply to the area by trowel or spatula in lifts of 1" to 1-1/2" (25 to 38 mm) before the neat primer coat becomes tack free. Allow each lift to reach initial set before applying subsequent lifts.

PRECAUTIONS/LIMITATIONS

- Store DURALFLEX LV indoors, protected from moisture, at temperatures between 50 °F and 90 °F (10 °C and 32 °C)
- Surface and ambient temperature during applications should be between 50 °F and 90 °F (10 °C and 32 °C)
- Material temperatures should be at least 50 °F (10 °C) and rising
- Working time and cure time will decrease as the temperature increases, and will increase as the temperature decreases
- Do not thin DURALFLEX LV
- DURALFLEX LV will discolor upon prolonged exposure to ultraviolet light and high-intensity artificial lighting.
- DURALFLEX LV is not to be used as a finished/aesthetic coating
- Do not use DURALFLEX LV for anchoring
- Maximum application thickness of DURALFLEX LV mortar is 1.5" (38 mm) per lift.
- In all cases, consult the product Safety Data Sheet before use

Rev. 12.23

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.