Master Format #: 00 00 00

# **EUCEM™ CGA 5 SPR**

# **HIGH PERFORMANCE GRINDING AID**



#### PRODUCT INFORMATION

#### **PACKAGING**

Available in 55 gal (208 L) drums, 264 gal (1000 L) totes, and bulk

#### **SHELF LIFE**

12 months

## SPECIFICATIONS/COMPLIANCES

ASTM C465

#### **TECHNICAL INFORMATION**

**Actives content: 92.0 - 96.0%** 

**Odor:** Characteristic

# **DESCRIPTION**

EUCEM CGA 5 SPR is a polyethanolamine modified glycol blend which has been specifically designed to improve the grinding of Portland cement. Depending on clinker and plant characteristics, EUCEM CGA 5 SPR is also very effective in improving cement flow characteristics and preventing pack set.

## **PRODUCT CHARACTERISTICS**

## **FEATURES & BENEFITS**

- Mill production is increased up to 15% depending on the efficiency of the equipment and the characteristics of the material to be ground.
- Grinding energy requirements and therefore grinding costs are reduced.
- The particle size distribution of the ground cement is improved, resulting in a more thorough hydration.
- Improved performance in both closed and open circuit systems at equal specific surface area or equal sieve residues.
- The mechanical strengths of cements are maintained or increased at all ages.
- Bulk density is increased.
- Powder flow characteristics are significantly improved before, during and after storage.
- Pack set tendencies and coating are substantially reduced.
- The risk of false set is reduced due to the lower grinding temperatures.

#### PRODUCT SPECIFICATION

% Solids	Specific Gravity @ 77°F (25 °C)	pH per Electrode
(ASTM C494)	(ASTM D1298)	@ 77°F (25 °C)
92.0 - 96.0	1.090 - 1.130	8.0 - 12.5

## **DIRECTIONS FOR USE**

## **DOSAGE**

The dosage range is from 0.40 lb per short ton (0.2 kg per metric ton) to 1.0 lb per short ton (0.5 kg per metric ton) of cement (active ingredients basis). Industrial trials are required to determine the optimum dosage. Dosages levels in excess of 2.0 lb per short ton (1.0 kg per metric ton) can cause dust emissions and should be avoided.

#### **PROCEDURE**

EUCEM CGA 5 ML may be introduced directly into the mill or onto the feed conveyor belt. A dosing pump is required to introduce the correct dosage into the mix. Our field technicians are ready to provide advice and assistance in the use of EUCEM CGA 5 ML.

# PRECAUTIONS/LIMITATIONS

- Store EUCEM CGA 5 SPR at temperatures above 32°F (0°C). If the product freezes, its properties can be recovered after thawing and agitating thoroughly.
- Do not store the product at temperatures above 100°F (38°C) for long periods.
- Refer to Safety Data Sheet for additional information.