

EUCOSHOT LR

SHOTCRETE MIX



EUCLID CHEMICAL

PACKAGING

50 lb (22.7 kg) bag (MTO)
Code: 105L 50
3,300 lb (1,500 kg) bulk bag
Code: 105L 99

APPROXIMATE YIELD

3,300 lb (1,500 kg) unit: 1.0 yd³ (0.76 m³)
per unit when mixed with 50gal (190 L)
of potable water.

MINIMUM/MAXIMUM APPLICATION THICKNESS

Typically 1/2 to 6 inches (1.2 to 15 cm)
per lift

CLEAN UP

Clean tools and equipment with water
before the material hardens.

SHELF LIFE

1 year in original, unopened package

DESCRIPTION

EUCOSHOT LR is a one component, shotcrete material. This cement based, modified mortar is designed for use on vertical and overhead surfaces by dry-mix shotcrete (gunite) application or by mixing with water and applying as a wet-mix shotcrete. EUCOSHOT LR is specially formulated for interior or exterior uses.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- One component material-ready to use with only the addition of water
- Lower resistivity formula for induced current applications
- Low shrinkage properties
- High abrasion resistance

PRIMARY APPLICATIONS

- Gunite projects
- Utility structures
- Tunnels
- Mining applications
- Rehabilitation and repair work

APPEARANCE

EUCOSHOT LR is a free flowing powder as packaged. The final finish appearance can be any texture consistent with that expected from sprayed concrete.

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C109 2" (50 mm) cubes	Compressive Strength	1 day 3,000 psi (21 MPa) 3 days 4,400 psi (30 MPa) 7 days 6,000 psi (41 MPa) 28 days 8,200 psi (56 MPa)
ASTM C348M	Flexural Strength	1 day 550 psi (3.8 MPa) 7 days 775 psi (5.3 MPa) 28 days 1,100 psi (7.6 MPa)
ASTM C882M	Shear Bond Strength	3 days 2,000 psi (14 MPa) 7 days 2,500 psi (17 MPa) 14 days 2,800 psi (19 MPa) 28 days 3,000 psi (21 MPa)
Germann Test	Direct Tensile Bond	14 days 350 psi (2.4 MPa) 28 days 425 psi (2.9 MPa)
ASTM C157 50% RH	Length Change	2 days - 0.003% 7 days - 0.003% 14 days - 0.007% 21 days - 0.025% 28 days - 0.033%
ASTM C1202	Rapid Chloride Permeability	7 days 4,000 coulombs 14 days 1,600 coulombs 21 days 975 coulombs 28 days 575 coulombs
ASTM C666 Procedure A	Freeze/Thaw Resistance	300 cycles > 98% RDM
ASTM C672	Scaling Resistance (Visual Rating)	10 cycles 0 20 cycles 0 30 cycles 0 50 cycles 0

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

DIRECTIONS FOR USE

Dry Shotcrete/Gunite: Set up dry process equipment in an area convenient to the placement site. Add EUCOSHOT LR powder directly to the gun. If dusting is objectionable, material may be pre-dampened prior to adding to gun. Gauge water at the nozzle and adjust to the desired consistency.

Placing Dry Shotcrete/Gunite: In general EUCOSHOT LR should be applied in accordance with the recommendations of ACI 506R "Guide to Shotcrete". Pay special attention to the angle of the application (i.e. 90°) and distance from the substrate, normally 2 ft (0.6 m) to 6 ft (1.8 m). Typical application depths range from 1/2" to 6" (12 to 150 mm). If placement at a depth greater than 6" (150 mm) is required, cross hatch the surface of the initial layer. After the surface has sufficiently hardened additional layers may be placed.

Mixing Wet Shotcrete: Add EUCOSHOT LR to water in the mixer drum (35 gallons [130 L] of water per 3,300 lb [1,500 kg] bulk bag of EUCOSHOT LR), mix for 2 minutes and add remaining water (up to 5 gal [20 L]). EUCON 37 can be used to reduce the amount of water required.

Placing-Wet Shotcrete: In general EUCOSHOT LR should be applied in accordance with the recommendations of ACI 506R "Guide to Shotcrete".

PRECAUTIONS/LIMITATIONS

- Do not allow applied shotcrete to freeze until the material has reached a minimum of 1,000 psi (7 MPa) compressive strength.
- When necessary, follow the recommendations in ACI 305R "Guide to Hot Weather Concreting" or ACI 306R "Guide to Cold Weather Concreting".
- Use only potable water at the nozzle.
- Minimum application thickness is 1/2" (13 mm).
- Minimum surface and ambient temperatures are 40 °F (5 °C) and rising at the time of application.
- For optimum results, condition material to 65 to 85 °F (18 to 29 °C).
- Store product in a dry place.
- In all cases, consult the Safety Data Sheet before use.

Rev. 07.22

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.