



# PSI CRIMPED STEEL FIBER MB

STEEL MACROFIBER WITH SYNTHETIC MONOFILAMENT MICROFIBER BLEND **EUCLID CHEMICAL**

## PRODUCT INFORMATION

### PACKAGING

24 lb (10.9 kg) bags;  
1728 lbs (784 kg) per pallet.

### SHELF LIFE

3 years in original, unopened package

### SPECIFICATIONS/COMPLIANCES

ASTM C1116  
ASTM A820, Type I/V  
ASTM D7508

### TECHNICAL INFORMATION

**Material:** Low carbon cold drawn steel wire/100% virgin polypropylene multi-length monofilament fiber

#### Typical Dosage Rate:

24 - 96 lb/yd<sup>3</sup> (14 - 57 kg/m<sup>3</sup>)

#### Available Lengths:

Steel Fiber - 1 ½" (38 mm)  
Synthetic Fiber - blend of ½" & ¾" (13 & 19 mm)

#### Aspect Ratio:

Steel Fiber - 34  
Synthetic Microfiber - N/A\*

#### Tensile Strength:

140 - 180 ksi (966 - 1242 MPa)

**Color:** Bright, clean wire with white synthetic fiber

\* Tensile strength and aspect ratio are not applicable for micro fibers based on ASTM D7508.

## DESCRIPTION

PSI Crimped Steel Fiber MB are low carbon, cold drawn steel wire fibers combined with 100% virgin multi-length monofilament polypropylene synthetic microfibers designed to provide concrete with plastic shrinkage crack protection, temperature and shrinkage crack control, enhanced flexural reinforcement, improved shear strength and increase the crack resistance of concrete. PSI Crimped Steel Fiber MB complies with ASTM C1116, Standard Specification for Fiber Reinforced Concrete and Shotcrete and ASTM A820, Standard Specification for Steel Fibers for Fiber Reinforced Concrete. This steel macrofiber blend will also improve impact, shatter, fatigue and abrasion resistance while increasing toughness of concrete. Dosage rates will vary depending upon the reinforcing requirements and can range from 24 to 96 lbs/yd<sup>3</sup> (14 to 57 kg/m<sup>3</sup>).

## PRODUCT CHARACTERISTICS

### FEATURES & BENEFITS

- Increases impact, shatter and abrasion resistance of concrete
- Reduces segregation, plastic settlement, and shrinkage cracking of concrete
- Provides three-dimensional reinforcement against macro-cracking
- Increases overall durability, fatigue resistance and flexural toughness
- Reduction of in-place cost versus wire mesh
- Easily added to concrete mixture at any time prior to placement

### PRIMARY APPLICATIONS

- Commercial and industrial slabs on ground
- Bridge decks, overlays and pavements
- Precast concrete applications
- Shotcrete, tunnel linings and slope stabilization
- Mass concrete and composite deck construction

## PRECAUTIONS/LIMITATIONS

- Use of fibers may cause an apparent loss in measured slump of concrete. This may be offset with the use of a water reducing admixture if necessary.
- Fibers should never be added to a "zero-slump" concrete. Ensure a minimum concrete slump of 3" (80 mm) prior to addition of any fiber material. Fibers may also be added in loose form to aggregate charging devices.
- In all cases, consult the Safety Data Sheet before use.

---

## DIRECTIONS FOR USE

PSI Crimped Steel Fiber MB can be added to the concrete mixture at any time prior to placement of the concrete. It is generally recommended to add any fiber material at the ready-mix concrete plant during batching. Fibers must be mixed with concrete for a minimum of four (4) to five (5) minutes at maximum mixing speed, depending on the mixer type, to ensure complete dispersion and uniformity. The addition of PSI Crimped Steel Fiber MB, at provided dosage rates, will decrease the measured slump of concrete; however, additional water should not be added. The use of water reducers and/or superplasticizers, such as the Eucon series or the Plastol series of admixtures may be necessary to maintain desired workability.

Add other admixtures independently from fiber addition. When used properly, and placed in a concrete mix of sufficient workability, the fibers will not adversely alter the compressive or flexural strength of concrete or shotcrete.

---

## CLEAN UP

Loose fiber material should be disposed in proper receptacles for refuse. Finishing equipment with fibers embedded in concrete should be thoroughly cleaned.

Rev. 05.21

**WARRANTY:** The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.