



INCRETE CONCRETE STAIN SEALER WB

WATER-BASED ACRYLIC PIGMENTED CONCRETE SEALER

EUCLID CHEMICAL

PACKAGING

1 gal (3.8 L) and 5 gal (18.9 L) units

YIELD

150 to 200 ft²/gal (3.67 to 4.90 m²/L) per coat. For best results, two thin coats of sealer are recommended.

APPEARANCE

35 standard colors - custom colors available upon request.

CLEAN UP

Use soap and warm water for cleaning tools/equipment immediately after use.

SHELF LIFE

2 years in original, unopened container

SPECIFICATIONS AND COMPLIANCES

VOC Content: <100 g/L

BRIEF OVERVIEW

INCRETE CONCRETE STAIN SEALER WB is an acrylic latex sealer designed to beautify, protect and seal concrete and masonry surfaces, resulting in a water and stain resistant surface. INCRETE CONCRETE STAIN SEALER WB is a blend of acrylic resins and the finest pigments available, providing durability and UV safe color fastness. INCRETE CONCRETE STAIN SEALER WB will seal and restore dull-looking concrete to a new luster while providing an easy-to-clean surface. INCRETE CONCRETE STAIN SEALER WB comes in a wide selection of colors for all environments.

PRODUCT CHARACTERISTICS

ADVANTAGES

- Exhibits excellent bond strength
- Exhibits excellent freeze-thaw resistance
- Superior abrasion resistance
- Perfect for all cementitious surfaces
- Deep penetrating sealer
- Low odor for interior use
- Eco-friendly formula

COMMON USES

- All unpainted masonry & concrete
- Pool decks Driveways and sidewalks
- Patios
- Architectural concrete
- Pre-cast concrete
- INCRETE SPRAY-DECK
- Residential, commercial & public projects
- 55 °F (12.8 °C) to 90 °F (32 °C)

COMMON APPLICATION METHODS

- Roller
- Sprayer

TECHNICAL INFORMATION

Typical Engineering Data

The following results were developed under laboratory conditions.

Drying time* at 73 °F (27.2 °C), 50% RH:	1 to 2 hours
Foot traffic	24 hours
Wheel traffic	48 hours
VOC content	<100 g/L
Adhesion to concrete.....	excellent
Solids content.....	42 to 48%
Min. Working Temperature	55 °F (12.8 °C)
Resistance to yellowing from UV light	excellent

**Low concrete or air temperature and/or high relative humidity will extend drying time.*

DIRECTIONS FOR USE

Application on a test area is highly recommended when unfamiliar with surface and/or product.

This extra step will determine if the surface is properly prepared, the probable coverage, and the best method suited for application.

PREPARATION

Concrete should be at least 28 days old. Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Remove any loose material and any coatings such as paint, curing agents, and sealers with INCRETE UNI-STRIPP sealer stripper. Clean with a cleaner/degreaser specifically designed for concrete and paver surfaces. Mechanically abrade the surface to achieve a surface profile equal to CSP 1-2 in accordance with ICRI Guideline 310.2. Properly clean profiled area. Avoid application during rainy, foggy, or very humid weather when water condensation forms on the surface.

MIXING

Always stir stain well before use and during application to prevent settling and to ensure proper dispersion of colorant. A variable-speed drill and a paddle mixer is the preferred method for this step.

ROLLER APPLICATION

Roll on first coat using a 1/4 in (6 mm) nap, lint-free roller. Apply using uniform, even strokes in the same direction. A second coat must be applied after the first coat has completely dried, usually a minimum of 1-2 hours.

SPRAY APPLICATION

Product may be sprayed using an airless sprayer with a medium tip size and very low pressure. For a uniform coverage, especially over decorative concrete, it is recommended to back roll the product after spraying. If conditions are windy or extremely hot, adjust technique to avoid "dry spraying" the surface. A second coat must be sprayed only after the first coat is dry.

PRECAUTIONS/LIMITATIONS

- Do not allow product to freeze. Store between 50 and 90 °F (10 to 32 °C).
- Excessive build-up of INCRETE CONCRETE STAIN SEALER WB or puddling of the product during application can lead to and discoloration.
- Do not apply when concrete surfaces or ambient temperatures are below 50 °F (10 °C) or if rain is expected within 12 hours after application.
- Not resistant to gasoline or other automotive fluids.
- Do not thin this product.
- For professional use only.
- In all cases, consult the Safety Data Sheet before use.

Rev. 12.22

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.